SeaRox SL 620

NEW NAME

Marine Firebatts 100

Firesafe Insulation

Product description

SeaRox SL 620 is a semi-rigid slab made of stone wool. The product can be supplied with reinforced alu foil or glass cloth.



Application

SeaRox SL 620 is primarily used as part of approved A constructions for Deck and Bulkhead.

Product Properties


	Performance		Norm
Thermal conductivity	T (°C)	10	EN 12667
	λ (W/mK)	0,035	
Nominal density	100 - 115 kg/m³		EN 1602 / IMO
Compressive strength	-		EN 826
Fire classification	Non-combustible Approved for A constructions Low Flame-Spread Properties		Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m²		EN 1609 AC
Max. Application Temperature	Wool: 750°C Facing: 80°C		-
Sound absorption directly mounted	α_w = 0,80 Thickness: 40 mm	α_w = 0,90 Thickness: 60 mm	ISO 354 (approximated) Evaluated after ISO 11 654
Facings (on request)	Reinforced alu foil White glass cloth 210 g/m² (GW200)		IMO A.653(16) (low flame - spread)

Dimensions

SeaRox SL 620:
Thickness (mm): 25,30,40,60 mm Length (mm): 1000 mm Width (mm): 600 mm

SeaRox SL 620 ALU:
Thickness (mm): 25,30,40,60 mm Length (mm): 1000 mm Width (mm): 600 mm

SeaRox SL 620 GW 200:
Thickness (mm): 25,40,60 mm Length (mm): 1000 mm Width (mm): 600 mm



0575/

Rockwool Technical Insulation reserves the right to make necessary product changes at anytime. Technical specifications are thus stated subject to change.

ROCKWOOL®
TECHNICAL INSULATION

Rockwool Technical Insulation
DK-2640 Hedehusene
Tel: +45 46 56 16 16
Fax. +45 46 56 16 04
export@rockwool.com
www.rockwool-rti.com
Part of Rockwool International A/S